



TruChem Company, Inc.  
6645 Singletree Drive  
Columbus, Ohio 43229  
614-888-2436  
www.truchem.com

## **T.C. 236**

### **Rust Preventative**

#### **DESCRIPTION**

T.C. 236 is a water displacing rust preventative. It leaves a dry-to-touch film, and will give 30 to 180 days indoor and outdoor rust prevention.

#### **APPLICATION**

Use at room temperature as a spray or in a dip tank. Parts should be relatively dry before application of T.C. 236. The film can be readily removed with solvent or alkaline cleaner if necessary. T.C. 236 can also be diluted with water as low as 10% by volume.

#### **SPECIFICATIONS**

Appearance	Dark Brown Liquid
Flash Point	>300° F.
Pounds/Gallon	7.340
Viscosity @ 100	35 to 40 SUS
Temperature	Room Temperature to 130° F.
Concentration	10% by Volume with Water

#### **SAFETY**

Do not take internally. For industrial use only. In case of accident, flush affected areas thoroughly with plenty of water. See a physician if irritation results.