



TruChem Company, Inc.  
6645 Singletree Drive  
Columbus, Ohio 43229  
614-888-2436  
www.truchem.com

## **T.C. 269**

### **Rust Preventative**

#### **DESCRIPTION**

T.C. 269 is a water-displacing, solvent-based rust preventative. It leaves a dry-to-touch film and will give a 30 to 120 days rust protection.

#### **APPLICATION**

Use at room temperature as a spray or in a dip tank. Parts should be relatively dry before application of T.C. 269. The film can be readily removed with solvent or alkaline cleaner if necessary.

#### **SPECIFICATIONS**

Appearance	Clear amber
Flash point	300°F
Pounds/Gallon	6.7
Viscosity @ 100	35 to 40 SUS
Temperature	Room temperature
Concentration	As is

#### **SAFETY**

Do not take internally. For industrial use only. In case of accident, flush