



T.C. 208-M

Soak Cleaner for Ferrous Base Metals

Non-Chelated

DESCRIPTION

An alkaline, granular and highly active cleaning compound.

APPLICATION

Recommended for the removal of drawing compounds, processing oils, smuts, greases, and lubricants from ferrous metal surfaces in soak tank applications.

PROPERTIES

High in emulsifying, dispersion and anti-deposition characteristics with excellent longevity. A heavy-duty soak cleaner for job shop or process plant operations.

CONDITIONS OF USE

Equipment	Mild steel tank
Concentration	6 to 10 ounces per gallon
Temperature	120° to 190°F
Time	5 to 10 minutes immersion

These conditions may be varied to suit individual cleaning requirements.

HANDLING

Wear proper long-sleeved protective clothing, chemical splash goggles, and rubber or neoprene gloves when handling or making up T.C. 208-M cleaning solutions. Avoid skin and eye contact. Always add T.C. 208-M to lukewarm water slowly and cautiously with adequate agitation. In case of accident, flush with water at once for at least 15 minutes and get medical attention. Remove contaminated clothing and wash before re-use. If ingested, drink copious quantities of water and call a physician. An eye/face fountain and safety deluge shower should be available in work area. For industrial use only.

KEEP OUT OF REACH OF CHILDREN.

DO NOT TAKE INTERNALLY.