



## **T.C. 228**

### **Alkaline Soak Cleaner and Rust Remover**

#### **DESCRIPTION**

T.C. 228 is an alkaline, granular and highly active cleaning compound.

#### **APPLICATION**

It is recommended for the removal of processing oils, smuts, greases, and lubricants from ferrous metal surfaces in soak tank applications. It may also be employed to remove light rust, paint and other organic coatings.

#### **PRODUCT PROPERTIES**

T.C. 228 is high in dispersion and emulsification with excellent longevity. It is a heavy duty soak cleaner for job shop or process plant operations. It is non-phosphate and biodegradable.

#### **CONDITIONS OF USE**

Equipment	Mild Steel Tank
Concentration	1/2 to 1 1/2 pounds per gallon
Temperature	175° to 200° F.
Contact Time	5 to 10 minutes immersion

These conditions may be varied to suit individual cleaning requirements.

#### **HANDLING**

Wear proper protective clothing, goggles and rubber gloves when handling or making T.C. 228 cleaning solutions. Avoid skin and eye contact. Always add T.C. 228 to lukewarm water slowly and cautiously with constant agitation. In case of accident, flush at once with copious quantities of water and call a physician. Remove contaminated clothing and wash before reuse. Do not take internally. If swallowed, do not induce vomiting. Give large amounts of water and at least an ounce of vinegar in an equal volume of water. Seek medical attention. An eye/face fountain and safety shower should be available in work area.